

**Ultramid® A3HG2**  
PA66-GF10

BASF

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Mold Shrinkage, MD	0.008	mm/mm	ASTM D 955
Density, 73°F	1200	kg/m <sup>3</sup>	ASTM D 792
Water Absorption, Equilibrium	7	%	ASTM D 570
Rheological properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	80 / *	cm <sup>3</sup> /10min	ISO 1133
Temperature	275 / *	°C	-
Load	5 / *	kg	-
Mechanical Properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	4600 / 2600	MPa	ISO 527
Stress at Break	100 / 60	MPa	ISO 527
Strain at Break	2.8 / 12	%	ISO 527
Impact Strength (Charpy), +23°C	30 / 92	kJ/m <sup>2</sup>	ISO 179/1eU
Notched Impact Strength (Charpy), +23°C	7 / 9	kJ/m <sup>2</sup>	ISO 179/1eA
Flexural Modulus (23°C)	4600 / -	MPa	ISO 178
Notched Impact Strength (Izod), 23°C	- / 7	kJ/m <sup>2</sup>	ISO 180/1A
<b>ASTM Data</b>			
Tensile Strength at Break	100 / -	MPa	ASTM D 638
Elongation at Break	3 / -	%	ASTM D 638
Flexural Modulus	4480 / -	MPa	ASTM D 790
Notched Impact Strength (Izod), 1/8 in	53 / -	J/m	ASTM D 256
Thermal Properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Melting Temperature (10°C/min)	260 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	210 / *	°C	ISO 75-1/-2
Burning Behav. at 1.5 mm Nom. Thickn.	HB / *	class	UL 94
Thickness tested	1.6 / *	mm	-
<b>ASTM Data</b>			
DTUL @ 264 psi	210	°C	ASTM D 648
Melting Temperature	260	°C	ASTM D 3418
Electrical Properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Relative permittivity, 1MHz	3.5 / 5.5	-	IEC 62631-2-1
Dissipation Factor, 1MHz	140 / 1600	E-4	IEC 62631-2-1
Volume Resistivity	1E13 / 1E10	Ohm*m	IEC 62631-3-1
Surface Resistivity	* / 1E10	Ohm	IEC 62631-3-2
Comparative tracking index	550 / -	-	IEC 60112
<b>ASTM Data</b>			
Volume Resistivity	1E13 / -	Ohm*cm	ASTM D 257
Other Properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Water Absorption	7 / *	%	Sim. to ISO 62
Humidity absorption	2.1 / *	%	Sim. to ISO 62
Density	1200 / -	kg/m <sup>3</sup>	ISO 1183
Material Specific Properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Viscosity number	148 / *	cm <sup>3</sup> /g	ISO 307, 1157, 1628

**Characteristics**

**Processing**

Injection Molding, Other Extrusion

**Applications**

Automotive, Electrical and Electronical

**Delivery form**

Pellets

**Disclaimer**

**Liability Exclusion**

These guide values are measured and provided by the product manufacturer and have been determined on standardised test specimens and can be affected by pigmentation, mould design and processing conditions. M-Base has taken the guide values from the producer's original Technical Data Sheet. **ALBIS AND M-BASE ARE THEREFORE NOT RESPONSIBLE FOR THE ACCURACY OF THE GUIDE VALUES AND CANNOT GIVE ANY WARRANTY WITH REGARD TO THEIR CORRECTNESS.**

Any information given on the chemical and physical characteristics of our products, including, without limitation, technical advice on applications, whether verbally, in writing or by testing the product, is given to the best of our knowledge and in good faith and does not exempt the buyer from carrying out their own investigations and tests in order to ascertain the product's specific suitability for the purpose intended.

The buyer is solely responsible for confirming the suitability of the product for a particular application, its utilization and processing and must observe any applicable laws and government regulations. **NO EXPRESS OR IMPLIED RECOMMENDATION OR WARRANTY IS GIVEN WITH REGARD TO THE SUITABILITY OF THE PRODUCT FOR A PARTICULAR APPLICATION, SUCH AS, BUT NOT LIMITED TO, SAFETY-CRITICAL COMPONENTS OR SYSTEMS.**

**Healthcare uses:** the supply of any product by ALBIS for any medical, pharmaceutical or diagnostic application is conditional to an assessment by ALBIS in terms of compliance with ALBIS' internal risk management policy – even for products which are in general designated for use in Healthcare applications.

**Important:** irrespective of product type or designation, ALBIS does not recommend or support the use of any products it supplies which fall into the following medical, pharmaceutical or diagnostic application categories:

- risk class III applications according to EU directive 93/42/EEC
- any bodily implant application for greater than 30 days
- any critical component in any medical device that supports or sustains human life.

At all times, our standard terms and conditions of sale apply.